
POLYCAB

CABLES





LT XLPE CABLE

TDS Doc.No:PIL/TE/250425/000823

DESIGN CODE : LVIS09AXAFYF001C120SA001S

Particulars		1 Core X 120 Sq.mm
Name of Manufacturer		Polycab India Ltd
Type of cable		A2XFaY
Voltage Grade V		1100
No of cores X size in sqmm		1 Core X 120 Sq.mm
Conductor		
a)	Material	H2/H4 Grade Aluminium as per Class 2 of IS: 8130/2013,latest
b)	Max. d.c. resistance of conductor at 20° C (ohm/km)	0.253
c)	Shape of the conductor	Stranded Compacted Circular
Insulation		
a)	Material	XLPE as per IS 7098(Pt-1)/88, Latest
b)	Nominal thickness (mm)	1.5
c)	Core identification	Natural
Armouring		
a)	Material	Aluminium
b)	Type of armouring	Flat Strip
c)	Nominal size of armour (mm)	4.0 x 0.8
d)	Tolerance on armour dimensions	± 10%
Outer Sheath		
a)	Material	Extruded FR PVC Type 'ST2' as per IS:5831/ 84
b)	Thickness (mm)	1.40 (Min.)
c)	Colour of outer sheath.	Black
Electrical Parameters		
a)	Max. a.c. resistance of conductor at 90° C (ohm/km)	0.325
b)	Calculated Cable reactance (ohm/km)	0.0904
c)	Impedance of cable (ohm/km)	0.337
d	Approx. Cable Capacitance (mfd/km)	0.66

Format ID: TE/QMS/F/07, R-00, Date: 16/03/2025

Maximum conductor temperature under normal operating conditions	90°C
Maximum conductor temperature at the termination of short circuit	250°C
Short Circuit rating of conductor for the duration of 1 sec (kA)	11.34
Continuous Current carrying capacities :-	
(a) In Ground at 30°C (A)	230
(b) In Air at 40°C (A)	276
Applicable Standard	IS 7098 Part I/88, IS 8130/2013, IS 5831/84 etc. with latest up to date amendments
Approx. overall diameter of the cable in mm	20.5 +/- 2.0
Minimum bending radius	15 times Overall diameter
Max. Tensile strength	
(i) for Cables pulled with stocking (Newtons)	9 x D^2, D is the cable OD in mm
(ii) for Cables pulled with pulling eyes (N)	3,600
Embossing	POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR YEAR POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR
Printing	CABLE SIZE CABLE TYPE WITH SEQUENTIAL MARKING at every one meter interval.
Standard Drum Length (Mtr.)	1000 ± 5%
Non- Standard Drum Length (Mtr.)	Maximum 5% of order quantity
FR PROPERTIES	
a) Oxygen Index	Min. 29% as per ASTM D- 2863
b) Temperature Index	Min. 250 Deg.C as per ASTM D- 2863
c) Flammability Test	As per IEC:332-I

Note:-The values given above are subject to tolerances as per the relevant standards

www.polycab.com | Toll Free No - 1800 267 0008 | Email: enquiry@polycab.com