
CABLES

POLYCAB





LT XLPE CABLE

TDS Doc.No:PIL/TE/250425/000777

DESIGN CODE : LVIS09AXUAYL003C095SA001S

Particulars		3 Core X 95 Sq.mm
Name of Manufacturer		Polycab India Ltd
Type of cable		A2XY
Voltage Grade V		1100
No of cores X size in sqmm		3 Core X 95 Sq.mm
Conductor		
a)	Material	H2/H4 Grade Aluminium as per Class 2 of IS: 8130/2013,latest
b)	Max. d.c. resistance of conductor at 20° C (ohm/km)	0.320
c)	Shape of the conductor	Stranded Compacted Sector
Insulation		
a)	Material	XLPE as per IS 7098(Pt-1)/88, Latest
b)	Nominal thickness (mm)	1.1
c)	Core identification	Red,Yellow,Blue
Inner Sheath		
a)	Material	Extruded PVC Type ST2 as per IS:5831/84
b)	Minimum thickness (mm)	0.4
Outer Sheath		
a)	Material	Extruded FR-LSH PVC Type 'ST2' as per IS:5831/ 84
b)	Thickness (mm)	2.2 (Nom.)
c)	Colour of sheath	Black
Electrical Parameters		
a)	Max. a.c. resistance of conductor at 90° C (ohm/km)	0.411
b)	Calculated Cable reactance (ohm/km)	0.0725
c)	Impedance of cable (ohm/km)	0.417
d	Approx. Cable Capacitance (mfd/km)	0.00
Maximum conductor temperature under normal operating conditions		90°C
Maximum conductor temperature at the termination of short circuit		250°C

Format ID: TE/QMS/F/07, R-00, Date: 16/03/2025

Short Circuit rating of conductor for the duration of 1 sec (kA)		8.98
Continuous Current carrying capacities :-		
(a)	In Ground at 30°C (A)	197
(b)	In Air at 40°C (A)	216
Applicable Standard		IS 7098 Part I/88,IS 8130/2013,IS 5831/84 etc. with latest up to date amendments
Approx. overall diameter of the cable in mm		31.5 ± 2.0
Minimum bending radius		12 times Overall diameter
Max. Tensile strength		
(i)	for Cables pulled with stocking (Newtons)	5 x D^2, D is the cable OD in mm
(ii)	for Cables pulled with pulling eyes (N)	8550
Embossing		POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH
Printing		YEAR POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH CABLE SIZE CABLE TYPE WITH SEQUENTIAL MARKING at every one meter interval.
Standard Drum Length (Mtr.)		500 ± 5%
Non- Standard Drum Length (Mtr.)		Maximum 5% of order quantity
FR-LSH PROPERTIES		
a)	Oxygen Index	Min. 29% as per ASTM D- 2863
b)	Temperature Index	Min. 250 Deg.C as per ASTM D- 2863
c)	Smoke Density Rating	Max. 60% as per ASTM D- 2843
d)	Acid Gas Generation	Max. 20% as per IEC- 754- 1
e)	Flammability Test	As per IEC:332-I

Note:-The values given above are subject to tolerances as per the relevant standards

www.polycab.com | Toll Free No - 1800 267 0008 | Email: enquiry@polycab.com